



DAIKOFCW 115B



HIGH YIELD STRENGTH STEELS
110ksi

DESCRIPTION

Basic flux cored wire for flat and horizontal position

The basic flux cored wire is formulated for welding high yield strength steels, with tensile strength higher than 770 MPa. Excellent resilience values at low temperatures, down to -60°C. It can be used in the construction of industrial machines, cranes, and other components that require high mechanical strength. The wire shows excellent weldability in flat and horizontal position, smooth and bright bead, very low spatter losses, easy to remove slag and exceptional mechanical properties even at low temperatures.

SPECIFICATIONS

EN ISO 18276-A	T 69 6 Mn2NiCrMo B M 3	AWS A5.36	E110T5
Shielding	M21	Positions	PA, PB, PC
Current	DC+	Packaging Type	B5300 spool

ASME QUALIFICATIONS

F-No (QW432)	6
A-No (QW442)	10

CHEM. COMP. %	DEFAULT	MECHANICAL PROPERTIES	MIN. PER STANDARD	PRODUCT
C	0.06	Tensile strength R_m MPa	760	840
Mn	1.4	Yield strength $R_{p0.2}$ MPa	690	690
Ni	2.2	Elongation A ($L_0=5d_0$) %	17	17
P	0.02	Impact Charpy ISO-V	47J @ -60°C	47J @ -60°C
S	0.02	Impact Charpy ISO-V	-	-
Mo	0.4			
Si	0.4			
Cu	0.1			
		WELDING PARAMETERS	1.2 mm	1.6 mm
		Ampere	160A - 280A	180A - 350A
		Voltage	18V - 30V	30V - 34V
		Packaging	Ø 1,2÷1,6mm	Ø 1,2÷1,6mm
		Packaging Type	B5300 spool	B5300 spool



The information contained in this technical data sheet is provided for information purposes only, based on data believed to be reliable at the date of publication, and does not constitute a warranty or contractual commitment. Actual performance may vary depending on operating and application conditions; it is the user's responsibility to verify the suitability of the product for the intended application. The manufacturer disclaims any liability for errors, omissions, or improper use. For the latest version, please refer to www.daikowelding.com.



110ksi

DESCRIPTION

HIGH YIELD STRENGTH STEELS

110ksi

APPLICATION

Ideal for joining high-strength thermomechanically refined and quenched and tempered fine-grain structural steels and tubes. The deposited metal provides excellent strength even at low temperatures when used with gas mixes. It has good deformability, making it particularly suitable for use in crane construction, buildings, and vehicles. It is critical to preheat according to base material and thickness; materials that could be welded with higher-strength consumables normally require a minimum preheat of 100 °C. For some HSLA steels, exceeding interpass temperatures of 200 °C can compromise strength and toughness. The post-weld heat treatment (PWHT) varies depending on the base material and the specified application.

ALLOY TYPE

Mn-Ni-Mo low alloy consumables for welding high strength steels with ultimate tensile strength up to 750 MPa (110 ksi).

MICROSTRUCTURE

The microstructure of all the consumables is predominantly ferrite; some will contain high proportions of acicular ferrite for optimum as-welded toughness

MATERIALS

For joining of quenched and tempered and thermomechanically rolled fine-grained structural steels. For use in building, crane and vehicle constructions.

EN W.Nr.: S690QL1, L555M, S690Q, S690QL, S690QL1, S650MC, S700MC

ASTM: A 514 Gr. F, H, Q

API: 5L X80, 5L X90, 5L X100

PROPRIETARY: N-A-XTRA® M 700 (ThyssenKrupp), Strenx® 700 (SSAB)

