



DAIKOFCW 309LP



AUSTENITIC STAINLESS STEELS
309L

DESCRIPTION

Rutile all position flux cored wire for dissimilar joints and buffer layers

Austenitic rutile flux cored wire for welding and cladding in all positions thanks to the fast-freezing slag. It offers excellent weldability, easy handling and slag control in all positions resulting in high productivity with outstanding welding performance. Characterized by self-releasing slag, very low spatter formation and increased travel speeds. It is designed for welding stainless steels of similar composition and for dissimilar welding such as welding stainless steel to carbon steel or low alloy steel. It is also used for buffer layer before cladding or hardfacing.

SPECIFICATIONS

EN ISO 17633-A	T 23 12 L P	AWS A5.22	E309LT1-1/4
Shielding	M21, C1	Positions	PA, PB, PC, PD, PE, PF, PG
Current	DC+	Packaging Type	B5300 spool

ASME QUALIFICATIONS

ASME QUALIFICATIONS	FERRITE	PREN	HARDNESS
F-No (QW432)	6	8-15 FN	23.3
A-No (QW442)	8		85HRB

CHEM. COMP. %

CHEM. COMP. %	DEFAULT	MECHANICAL PROPERTIES	MIN. PER STANDARD	PRODUCT
C	0.02	Tensile strength R_m MPa	510	580
Mn	0.8	Yield strength $R_{p0.2}$ MPa	320	450
Ni	12.6	Elongation A ($L_0=5d_0$) %	25	30
Cr	23.3	Impact Charpy ISO-V	-	50J @ -20°C
P	0.02	Impact Charpy ISO-V	-	-
S	0.01			
Si	0.45			

WELDING PARAMETERS

	1.2 mm	1.6 mm
Ampere	120A - 280A	200A - 350A
Voltage	22V - 30V	26V - 30V
Packaging	Ø 1,2÷1,6mm	Ø 1,2÷1,6mm
Packaging Type	B5300 spool	B5300 spool

NOTES

D200 spool and Ø 1,0 mm available upon request.



The information contained in this technical data sheet is provided for information purposes only, based on data believed to be reliable at the date of publication, and does not constitute a warranty or contractual commitment. Actual performance may vary depending on operating and application conditions; it is the user's responsibility to verify the suitability of the product for the intended application. The manufacturer disclaims any liability for errors, omissions, or improper use. For the latest version, please refer to www.daikowelding.com.



309L

DESCRIPTION

AUSTENITIC STAINLESS STEELS

309L

APPLICATION

****Bearing layers and claddings on steels****: Ideal for overlays on carbon-manganese steels, mild or low alloy steels, and for joining clad plates in 304L/321. Successive layers are applied with electrodes selected to match the cladding, such as 308L or 347. ****Dissimilar connections****: Thanks to its tolerance to dilution, it is used to join stainless steels like 410, 304L, 321, and 316L with mild and low alloy steels for reinforcements, brackets, and other accessories. Not suitable for service temperatures above 400 °C. It is also suitable for welding 12% Cr ferritic steels, such as Cromwell 3CR12, both among themselves and with other steels. ****Similar metal joints****: Wrought and cast steels, type 23Cr-12Ni (e.g., ASTM 309 and CH8, BS 309S24 and 309C30), can be welded when corrosion resistance below 400 °C is required. For high-temperature structural applications, a welding metal with a higher carbon content and reduced ferrite is necessary. Preheating and interpass temperatures depend on the hardenability of the base material. As a guide, no preheating is necessary for mild steels; on hardenable ones, the temperature can reach up to 250 °C.

ALLOY TYPE

24%Cr-13%Ni (309L) austenitic stainless for dissimilar joint buffer layers etc.

MICROSTRUCTURE

Austenite with ferrite in the range 8-20FN. GMAW tends to have lower ferrite (8-15 FN) than the MMA and FCW consumables.

MATERIALS

Mainly used under high dilution conditions, particularly dissimilar welds between stainless and CMn steels.

