



DAIKOFCW 97



HIGH YIELD STRENGTH STEELS
110ksi

DESCRIPTION

Rutile all position flux cored wire

Rutile seamless flux cored wire formulated for welding high yield strength steels, with tensile strength higher than 770 MPa. Excellent resilience values at low temperatures, down to -40°C. It can be used in the construction of industrial machines, cranes, and other components that require high mechanical strength. Self-releasing slag requiring less cleaning and pickling, very low spatter formation and increased travel speeds allow to obtain noticeable savings in time and costs.

SPECIFICATIONS

AWS A5.29	E111T1-K3MJ	Shielding	M21
Positions	PA, PB, PC, PD, PE, PF, PG	Current	DC+
Packaging Type	B5300 spool		

ASME QUALIFICATIONS

F-No (QW432)	6
A-No (QW442)	-

CHEM. COMP. %	DEFAULT	MECHANICAL PROPERTIES	PRODUCT	
C	0.07	Tensile strength R _m MPa	870	
Mn	2	Yield strength R _{p0.2} MPa	740	
Ni	2	Elongation A (L ₀ =5d ₀) %	18	
P	0.01	WELDING PARAMETERS	1.2 mm	1.6 mm
S	0.01		Ampere	160A - 280A
Mo	0.4	Voltage	18V - 30V	30V - 34V
Si	0.4	Packaging	Ø 1,2÷1,6mm	Ø 1,2÷1,6mm
Cu	0.15	Packaging Type	B5300 spool	B5300 spool



The information contained in this technical data sheet is provided for information purposes only, based on data believed to be reliable at the date of publication, and does not constitute a warranty or contractual commitment. Actual performance may vary depending on operating and application conditions; it is the user's responsibility to verify the suitability of the product for the intended application. The manufacturer disclaims any liability for errors, omissions, or improper use. For the latest version, please refer to www.daikowelding.com.





110ksi

DESCRIPTION

HIGH YIELD STRENGTH STEELS
110ksi

APPLICATION

Ideal for joining high-strength thermomechanically refined and quenched and tempered fine-grain structural steels and tubes. The deposited metal provides excellent strength even at low temperatures when used with gas mixes. It has good deformability, making it particularly suitable for use in crane construction, buildings, and vehicles. It is critical to preheat according to base material and thickness; materials that could be welded with higher-strength consumables normally require a minimum preheat of 100 °C. For some HSLA steels, exceeding interpass temperatures of 200 °C can compromise strength and toughness. The post-weld heat treatment (PWHT) varies depending on the base material and the specified application.

ALLOY TYPE

Mn-Ni-Mo low alloy consumables for welding high strength steels with ultimate tensile strength up to 750 MPa (110 ksi).

MICROSTRUCTURE

The microstructure of all the consumables is predominantly ferrite; some will contain high proportions of acicular ferrite for optimum as-welded toughness

MATERIALS

For joining of quenched and tempered and thermomechanically rolled fine-grained structural steels. For use in building, crane and vehicle constructions.

EN W.Nr.: S690QL1, L555M, S690Q, S690QL, S690QL1, S650MC, S700MC

ASTM: A 514 Gr. F, H, Q

API: 5L X80, 5L X90, 5L X100

PROPRIETARY: N-A-XTRA® M 700 (ThyssenKrupp), Strenx® 700 (SSAB)

