



DESCRIPTION

Basic flux cored wire for flat and horizontal position

Basic flux cored wire designed for prolonged elevated temperature service up to about 450°C for welding of low alloy and creep resistant steels. Application area includes boiler, pressure vessel, tanks, pipeline, and crane constructions as well as in structural steel engineering. It shows excellent weldability in flat and horizontal position, smooth and bright bead, very low spatter losses, easy to remove slag and exceptional mechanical properties even at low temperatures.

SPECIFICATIONS

EN ISO 17634-A	T 46 6 Mo B M 3	AWS A5.36	E80T5-M21P8-A1
Shielding	M21	Positions	PA, PB, PC
Current	DC+	Packaging Type	B5300 spool

ASME QUALIFICATIONS

F-No (QW432)	6
A-No (QW442)	2

CHEM. COMP. %	DEFAULT	MECHANICAL PROPERTIES	MIN. PER STANDARD	PRODUCT
C	0.06	Tensile strength R_m MPa	550	620
Mn	1.4	Yield strength $R_{p0.2}$ MPa	460	470
P	0.02	Elongation A ($L_0=5d_0$) %	17	20
S	0.02	Impact Charpy ISO-V	47J @ -60°C	47J @ -60°C
Mo	0.5	Impact Charpy ISO-V	-	-
Si	0.5			
Cu	0.15			
		WELDING PARAMETERS	1.2 mm	1.6 mm
		Ampere	100A - 300A	160A - 420A
		Voltage	16V - 28V	31V - 35V
		Packaging	Ø 1,2÷1,6mm	Ø 1,2÷1,6mm
		Packaging Type	B5300 spool	B5300 spool

NOTES

Preheat and interpass temperature <200°C.



The information contained in this technical data sheet is provided for information purposes only, based on data believed to be reliable at the date of publication, and does not constitute a warranty or contractual commitment. Actual performance may vary depending on operating and application conditions; it is the user's responsibility to verify the suitability of the product for the intended application. The manufacturer disclaims any liability for errors, omissions, or improper use. For the latest version, please refer to www.daikowelding.com.



0.5Mo

DESCRIPTION

CREEP RESISTING STEELS

0.5Mo

APPLICATION

The alloy with a nominal 0.5% molybdenum offers a significant improvement in high-temperature performance compared to carbon-manganese steels (C-Mn). It is widely used in the **fabrication of vessels** and **pipelines** requiring resistance to creep rupture and ductility at temperatures up to about 450 °C. The molybdenum content also enhances resistance to hydrogen attack, making it ideal for use in chemical processing plants. The mechanical properties of the weld metal, both in the as-welded and stress-relieved conditions, are excellent for welding technical structural and general structural steels intended for ambient or sub-zero temperature service. Therefore, these consumables are closely related to high-strength manganese-molybdenum alloy steels. Preheat and interpass temperatures generally range from 100 °C to 250 °C, depending on the thickness of the material being welded and the degree of restraint. Post-weld heat treatment (PWHT) for tempering can vary depending on the applied code; extremes range from 550 °C to 720 °C, with the most common range being from 630 °C to 670 °C. For materials up to 20 mm thick, some codes allow omitting the PWHT.

ALLOY TYPE

Ferritic creep resisting 0.5%Mo steels for elevated temperature service.

MICROSTRUCTURE

In the stress-relieved condition the microstructure consists of acicular ferrite with some tempered bainite.

MATERIALS

EN W.Nr.: 10028-2 gr. 16Mo3 (1.5415), 16Mo5 (1.5423), 10MnMo 4 5 (1.5424), 11MnMo 4 5 (1.5425), GS-22Mo 4 (1.5419)

ASTM: A335 gr. P1, A209 & A 250 gr. T1, A336 gr. F1, A204 gr. A, B, C, A217 gr. WC1, A352 gr. LC1

