



# DAIKOMCW 385



SUPERAUSTENITIC STEELS  
904L

## DESCRIPTION

metal cored wire for flat and horizontal position for 904L steel

Virtually spatter free in the spray-arc range. Particularly suitable for robotic applications for welding and cladding austenitic stainless alloys of the 20% Cr, 25% Ni, 5% Mo, 1.5% Cu, low C types. Its weld metal has good resistance to stress corrosion and intergranular corrosion and shows very good resistance to attack in non-oxidising acids. The resistance to crevice corrosion is better than that of ordinary 18% Cr, 8% Ni, Mo steels. The alloy is widely used in many applications related to the process industry.

## SPECIFICATIONS

EN ISO 17633-A	T Z 20 25 5 Cu L M I11	AWS A5.22	EC385
Shielding	M21	Positions	PA, PB, PC
Current	DC+	Packaging Type	B5300 spool

## ASME QUALIFICATIONS

		PREN
F-No (QW432)	6	37.5
A-No (QW442)	-	

CHEM. COMP. %	DEFAULT	MECHANICAL PROPERTIES	MIN. PER STANDARD	PRODUCT
C	0.02	Tensile strength R <sub>m</sub> MPa	510	660
Mn	2.5	Yield strength R <sub>p0.2</sub> MPa	320	410
Ni	25	Elongation A (L <sub>0</sub> =5d <sub>0</sub> ) %	25	35
Cr	21	Impact Charpy ISO-V	-	50J @ -196°C
P	0.02	Impact Charpy ISO-V	-	-
S	0.008			
Mo	5			
Si	0.4			
Cu	1.5			
		WELDING PARAMETERS	1.2 mm	1.6 mm
		Ampere	130A - 280A	200A - 350A
		Voltage	22V - 30V	28V - 32V
		Packaging	Ø 1,2÷1,6mm	Ø 1,2÷1,6mm
		Packaging Type	B5300 spool	B5300 spool

## NOTES

D200 spool and Ø 1,0 mm available upon request.



The information contained in this technical data sheet is provided for information purposes only, based on data believed to be reliable at the date of publication, and does not constitute a warranty or contractual commitment. Actual performance may vary depending on operating and application conditions; it is the user's responsibility to verify the suitability of the product for the intended application. The manufacturer disclaims any liability for errors, omissions, or improper use. For the latest version, please refer to [www.daikowelding.com](http://www.daikowelding.com).



# 904L

## DESCRIPTION

SUPERAUSTENITIC STEELS

904L

### APPLICATION

This consumable is designed to provide a fully austenitic low-carbon weld metal, enriched with molybdenum and copper. It is renowned for its excellent corrosion resistance in acidic environments, such as sulfuric and phosphoric, as well as in other types of both inorganic and organic acids. However, it is not the ideal choice for environments with concentrated nitric acid. For applications requiring chloride pitting resistance, the use of nickel-based over-alloyed weld metals, such as Alloy 625, is recommended. It is the preferred weld metal for certain low-alloy austenitics, such as Creusot UHB 34L and UHB 734L, especially when used with wet-process phosphoric acid. Typical applications include tanks and process vessels, piping systems, agitators, and rotors, as well as cast pumps and valves used for the production of fertilizers, phosphoric, sulfuric, and acetic acid. It is also suitable for brackish and marine environments and in some offshore applications, such as overlays on mild and low-alloy steels. No preheat or post-weld heat treatment (PWHT) is necessary; however, it is essential to control the interpass temperature up to a maximum of 150 °C, paying particular attention to the heat input, especially when using large diameter SMAW electrodes.

### ALLOY TYPE

904L is a nominally 20%Cr-25%Ni-5%Mo-2%Cu alloy with good corrosion resistance.

### MICROSTRUCTURE

In the as-welded condition the weld metal microstructure is fully austenitic.

### MATERIALS

Suitable for copper-free variants of the listed alloys and also to overmatch leaner alloys such as 317L, 317LN, 317LM, 317LMN, 1.4439, 1.4440 and 531726.

**EN W.Nr.:** 1.4505 (X4NiCrMoCuNb20-18-2), 1.4506 (X5NiCrMoCuTi 20-18), 1.4536 (GX2NiCrMoCuN25-20), 1.4539 (X1CrNiMoCuN25-20-5), 1.4585 (G-X7CrNiMoCuNb1818), 1.4500 (G-X7NiCrMoCuNb2520)

**ASTM:** N08904

**PROPRIETARY:** Uddelholm 904L (voestalpine), 2RK65 (Sandvik), Cronifer 1925LC (VDM), 254SLX (Outokumpu), Uranus® B6, B6M (Industeel)

