



DAIKOWM 276



NICKEL ALLOYS
C276

DESCRIPTION

Solid wire for Nickel based alloy C276

Wire rod formulated to match the composition and properties of alloy C276. It is also used for surfacing of steel. The weld metal has high resistance in a wide range of media and exceptional resistant to pitting and crevice corrosion. Applications include pumps, valves, pipework and vessels in chemical process plant, equipment for flue gas desulphurisation and for offshore in oil & gas field. Useful properties from -269°C to above 1000°C are achieved.

SPECIFICATIONS

EN ISO 18274	S Ni 6276	AWS A5.14	ERNiCrMo-4
Shielding	I1, I3	Positions	PA, PB, PC, PD, PE, PF, PG
Current	DC+	Packaging Type	Drums, DIN 760 reel, B300, D200 and D100 spools.

ASME QUALIFICATIONS

		PREN
F-No (QW432)	43	74.51
A-No (QW442)	-	

CHEM. COMP. %	DEFAULT	MECHANICAL PROPERTIES	MIN. PER STANDARD	PRODUCT
C	0.01	Tensile strength R _m MPa	690*	720
Mn	0.2	Yield strength R _{p0.2} MPa	0	450
Ni	59	Elongation A (L ₀ =5d ₀) %	0	45
Cr	16.1	Impact Charpy ISO-V	-	80J @ -196°C
Nb	3.7	Impact Charpy ISO-V	-	-
V	0.05			
P	0.008			
S	0.002			
Mo	16			
Si	0.2			
Cu	0.01			
Fe	5.2			
W	3.4			

	1.0 mm	1.2 mm
WELDING PARAMETERS		
Ampere	140A - 200A	150A - 210A
Voltage	23V - 27V	25V - 29V
Packaging	Ø 0,8÷1,6mm	Ø 0,8÷1,6mm
Packaging Type	Drums, DIN 760 reel, B300, D200 and D100 spools.	Drums, DIN 760 reel, B300, D200 and D100 spools.

NOTES

* Typical weld metal tensile strength, only as indication.



The information contained in this technical data sheet is provided for information purposes only, based on data believed to be reliable at the date of publication, and does not constitute a warranty or contractual commitment. Actual performance may vary depending on operating and application conditions; it is the user's responsibility to verify the suitability of the product for the intended application. The manufacturer disclaims any liability for errors, omissions, or improper use. For the latest version, please refer to www.daikowelding.com.



C276

DESCRIPTION

NICKEL ALLOYS

C276

APPLICATION

The weld deposit perfectly matches the C276 base alloy, composed of Ni-15%Cr-16%Mo-4%W-5%Fe. The carbon (C) and silicon (Si) content is carefully controlled to minimize the formation of carbide precipitates and intermetallic phases. Cast alloy variants generally present higher levels of carbon and silicon, but repair welds are typically heat-treated for solutionizing to ensure optimal corrosion resistance. The C276 alloy offers excellent corrosion resistance in a wide range of acids and salts, under both oxidizing and reducing conditions. These include hydrochloric acid, hydrofluoric acid, hypochlorites, chlorides, wet chlorine gas, sulfuric acid, phosphoric acid, and numerous organic acids. It demonstrates exceptional pitting and crevice corrosion resistance in saltwater and shows high resistance to chloride-induced stress corrosion cracking, superior to alloy 62. Its excellent mechanical properties at temperatures down to -196 °C make it ideal for welding cryogenic plants with a Ni content between 5-9%. Typical applications include use in **pumps, valves, piping, and vessels** for aggressive environments in chemical processing plants, as well as in flue gas desulfurization equipment and the offshore oil and gas sector. No preheat is necessary; the interpass temperature should preferably be maintained below 100 °C, and the heat input must be limited to 1.5 kJ/mm.

ALLOY TYPE

Alloy C276 is a Ni-15%Cr-16%Mo-4%W-5%Fe nickel base alloy.

MICROSTRUCTURE

In the as-welded condition the weld metal consists of austenite with some carbides.

MATERIALS

EN W.Nr.: 2.4819 (NiMo16Cr15W), 2.4883 (G-NiMo16Cr)

ASTM: A494 CW-12MW, A743/A744 CW-12M

UNS: N10276

PROPRIETARY: Hastelloy® Alloy C-276 (Haynes International Inc), Inconel® Alloy C-276 (Special Metals), Nicrofer 5716hMoW (VDM)

