



DAIKOWS 2594Cu



DUPLEX - SUPERDUPLEX
ZERON 100

DESCRIPTION

Solid superduplex stainless wire rod for welding Zeron® 100 alloy

Superduplex filler metal matching the proprietary Zeron® 100 alloy. The presence of Cu+W in this alloy provides superior resistance to sulphuric and hydrochloric acids when compared to similar alloys without these additions. Offshore applications exploit the high resistance to pitting and stress corrosion cracking in seawater. It is also highly resistant to caustic alkalis and phosphoric acid. Widely used in oil and gas production and process.

SPECIFICATIONS

EN ISO 14343-A	S 25 9 4 N L	AWS A5.9	ER2594
Shielding	DAIKOFLUX 900-W	Positions	PA, PB, PC
Current	DC/AC	Packaging Type	K415 spool and drums.

ASME QUALIFICATIONS

FERRITE

PREN

F-No (QW432)	6	% 30-60	40.56
A-No (QW442)	-		

CHEM. COMP. %

DEFAULT

MECHANICAL PROPERTIES

MIN. PER STANDARD

PRODUCT

C	0.02	Tensile strength R _m MPa	620	860
Mn	0.6	Yield strength R _{p0.2} MPa	550	650
Ni	9.1	Elongation A (L ₀ =5d ₀) %	18	24
Cr	25	Impact Charpy ISO-V	-	40J @ -40°C
N	0.23	Impact Charpy ISO-V	-	-
P	0.02	WELDING PARAMETERS 2.4 mm		
S	0.015	Ampere	250A - 420A	
Mo	3.6	Voltage	28V - 32V	
Si	0.3	Packaging	Ø 2,0÷4,0mm	
Cu	0.6	Packaging Type	K415 spool and drums.	
W	0.65			

NOTES

SAW mechanical properties depend on wire/flux combination, refer to flux TDS.





ZERON 100

DESCRIPTION

DUPLEX - SUPERDUPLEX
ZERON 100

APPLICATION

Zeron® 100 stands out for its extraordinary ability to resist corrosion and erosion in a wide range of aggressive environments. The special Cu+W combination significantly improves resistance to sulfuric and hydrochloric acids, compared to similar alloys without such additives. Thanks to its high resistance to pitting and stress corrosion cracking, Zeron® 100 is widely used in offshore applications, especially in seawater contexts. This material also offers excellent resistance to caustic alkalis and phosphoric acid. Its service temperature range generally varies between -50 °C and 280 °C, with the upper limit due to thermal instability (450 °C and sigma phase embrittlement). Zeron® 100 is highly valued in the oil and gas production sector and is used in a wide range of applications, including process piping, risers, manifolds, pressure vessels, valves, pumps, desalination plants, flue gas desulfurization (FGD) systems, and in the mining, chemical, and pharmaceutical industries. Furthermore, Zeron® 100 wires are ideal for joining supermartensitic stainless steels.

ALLOY TYPE

25%Cr ferritic-austenitic superduplex stainless steels matching the proprietary Zeron® 100 alloy.

MICROSTRUCTURE

Austenite-ferrite duplex microstructure in AW or solution annealed condition with an approximate 30- 60% ferrite level, depending on heat cycle conditions.

MATERIALS

EN W.Nr.: 1.4508, 1.4501, 1.4469

ASTM: A890 6A, A182 F55, A890 5A

UNS: S32760, J93380, S32750, S32550, S32520, S39274, S32950, J93404

PROPRIETARY: Zeron 100 (Rolled Alloys) DP3W (Nippon Steel Corporation), 7-Mo Plus (Carpenter), SAF 2507 (Sandvik)

WELDING & PWHT

For welding Zeron® 100, preheating is generally not required. The interpass temperature should not exceed 150 °C. A heat input between 1.0 and 2.0 kJ/mm (based on the material thickness) is considered optimal, though many industrial codes set a maximum limit of 1.5 or 1.75 kJ/mm. While welds in wrought duplex stainless steels are usually left as is, major repairs on castings often require a solution treatment. Field tests confirm that good properties are obtained by following a water quench treatment at 1120 °C for a period between 3 and 6 hours.

