



# DAIKOWS 308L



AUSTENITIC STAINLESS STEELS  
308L

## DESCRIPTION

### Solid wire for 304L base materials

These consumables are used to weld 18/8 stainless steels. Mainly applications include food industries, pharmaceutical equipment and general fabrication. Typical service temperatures are -100°C to 400°C. Reduced carbon levels offer increased resistance to inter-granular corrosion. Very good corrosion resistance under fairly severe conditions, such as in oxidizing acids and cold or dilute reducing acids. The wire can also be used for welding titanium and niobium stabilized steels such as 321 and 347 when the construction is used at temperatures not exceeding 400°C.

## SPECIFICATIONS

EN ISO 14343-A	S 19 9 L	AWS A5.9	ER308L
Certifications	CE	Shielding	DAIKOFLUX 900-W
Positions	PA, PB, PC	Current	DC/AC
Packaging Type	K415 spool and drums.		

## ASME QUALIFICATIONS

F-No (QW432)	6
A-No (QW442)	8

## FERRITE

3-12 FN
---------

## PREN

20.33
-------

## HARDNESS

76HRB
-------

## CHEM. COMP. %

### DEFAULT

C	0.01
Mn	1.7
Ni	10
Cr	20
P	0.015
S	0.01
Mo	0.1
Si	0.4
Cu	0.15

## MECHANICAL PROPERTIES

	MIN. PER STANDARD	PRODUCT
Tensile strength $R_m$ MPa	510	570
Yield strength $R_{p0.2}$ MPa	320	445
Elongation A ( $L_0=5d_0$ ) %	25	40
Impact Charpy ISO-V	-	50J @ -196°C
Impact Charpy ISO-V	-	-

## WELDING PARAMETERS

	2.4 mm
Ampere	300A - 400A
Voltage	27V - 33V
Packaging	Ø 2,0÷4,0mm
Packaging Type	K415 spool and drums.

## NOTES

SAW mechanical properties depend on wire/flux combination, refer to flux TDS.



The information contained in this technical data sheet is provided for information purposes only, based on data believed to be reliable at the date of publication, and does not constitute a warranty or contractual commitment. Actual performance may vary depending on operating and application conditions; it is the user's responsibility to verify the suitability of the product for the intended application. The manufacturer disclaims any liability for errors, omissions, or improper use. For the latest version, please refer to [www.daikowelding.com](http://www.daikowelding.com).



# 308L

DESCRIPTION

AUSTENITIC STAINLESS STEELS  
308L

## APPLICATION

The 308L subfamily is specifically designed for the welding of 18/8 series stainless steels, including 301, 302, 303, and 304LN that contain nitrogen, as well as titanium-stabilized steels such as 321. The operating temperature range generally extends from -100°C to about 400°C. These consumables are ideal for a variety of applications ranging from the food sector to breweries, pharmaceutical equipment, construction and general building, to nuclear engineering. However, 308L products are not suitable for use with 304/304H steels in structural applications requiring high temperatures; for these needs, it is recommended to consult technical sheets C-10 and C-12. Similarly, for cryogenic applications (-196°C), it is advisable to refer to technical sheet B-37. No preheat is necessary and the maximum interpass temperature is set to 250°C; also, no post-weld heat treatment (PWHT) is required.

## ALLOY TYPE

308L austenitic stainless steels for joining 304L base materials.

## MICROSTRUCTURE

Austenite with a controlled level of ferrite, normally in the range 3-12FN depending on the application.

## MATERIALS

**EN W.Nr.:** 1.4306 (X2CrNi19-11), 1.4301 (X5CrNi18-10), 1.4311 (X2CrNiN18-10), 1.4308 (X5CrNi19-10), 1.4541 (X6CrNiTi18-10), 1.4543 (X 3 CrNiCuTi 12-9), 1.4561 (X1CrNiMoTi18-13-2), 1.4550 (X6CrNiNb18-10)+

**ASTM:** 304L, 304, 304LN, CF3, CF8, 321, 347

**UNS:** S30403, S30400, S30453, S32100, S34700

## WELDING & PWHT

Supply of welding consumables with optimized performance for strength and durability, including special alloys for high-temperature applications.



The information contained in this technical data sheet is provided for information purposes only, based on data believed to be reliable at the date of publication, and does not constitute a warranty or contractual commitment. Actual performance may vary depending on operating and application conditions; it is the user's responsibility to verify the suitability of the product for the intended application. The manufacturer disclaims any liability for errors, omissions, or improper use. For the latest version, please refer to [www.daikowelding.com](http://www.daikowelding.com).