



DAIKOWS 9CrMo



CREEP RESISTING STEELS
9CrMo

DESCRIPTION

9%Cr-1%Mo solid wire for elevate temperature service

Submerged arc welding wire designed for 9% Cr 1% Mo alloyed steels and steels for pressurized hydrogen service, particularly in oil refineries prolonged elevated temperature service up to about 650°C, especially in oil refineries (piping, heat exchangers, pressure vessels, boiler superheater). Designed for high strength and improved corrosion resistance in superheated steam, hot hydrogen gas and high sulphur crude oils where higher performance than 5% chromium, 0.5% molybdenum steels is required.

SPECIFICATIONS

EN ISO 24598-A	S CrMo9 FB	AWS A5.23	EB8
Shielding	DAIKOFLUX 982	Positions	PA, PB, PC
Current	DC/AC	Packaging Type	K415 spool and drums.

ASME QUALIFICATIONS

F-No (QW432)	6
A-No (QW442)	5

CHEM. COMP. %	DEFAULT	MECHANICAL PROPERTIES	MIN. PER STANDARD	PRODUCT	
C	0.07	Tensile strength R_m MPa	590	680	
Mn	0.5	Yield strength $R_{p0.2}$ MPa	435	590	
Cr	9	Elongation A ($L_0=5d_0$) %	17	23	
P	0.01	Impact Charpy ISO-V	47J @ 20°C	50J @ 20°C	
S	0.01	Impact Charpy ISO-V	-	-	
Mo	1				
Si	0.2				
Cu	0.15				
		WELDING PARAMETERS	2.4 mm	3.2 mm	4.0 mm
		Ampere	350A - 450A	430A - 530A	480A - 580A
		Voltage	27V - 31V	27V - 31V	27V - 31V
		Packaging	Ø 2,0÷4,0mm	Ø 2,0÷4,0mm	Ø 2,0÷4,0mm
		Packaging Type	K415 spool and drums.	K415 spool and drums.	K415 spool and drums.

NOTES

Preheat and interpass temperature 200 to 300 °C, post-weld heat treatment of test piece 740 to 780°C for 2h. SAW mechanical properties depend on wire/flux combination, refer to flux TDS.



The information contained in this technical data sheet is provided for information purposes only, based on data believed to be reliable at the date of publication, and does not constitute a warranty or contractual commitment. Actual performance may vary depending on operating and application conditions; it is the user's responsibility to verify the suitability of the product for the intended application. The manufacturer disclaims any liability for errors, omissions, or improper use. For the latest version, please refer to www.daikowelding.com.



9CrMo

DESCRIPTION

CREEP RESISTING STEELS

9CrMo

APPLICATION

Designed for high-temperature applications, 9CrMo offers a reasonable degree of corrosion resistance in superheated steam, hot hydrogen gas, and high-sulfur crude oil, surpassing the performance of 5% Cr-0.5% Mo steels. It is particularly suitable for welding heat-treatable steels, quenched and subsequently tempered. Ideal for piping and components resistant to caustic embrittlement, it maintains its effectiveness up to service temperatures of 600 °C. It is primarily used for **boiler superheater piping, heat exchangers, pipelines** and **pressure vessels in oil refineries and power plants**.

ALLOY TYPE

9%Cr-1%Mo martensitic alloy for elevated temperature service.

MICROSTRUCTURE

In the PWHT condition the microstructure consists of tempered bainite.

MATERIALS

EN W.Nr.: X12CrMo 9 1 (1.7386), X7CrMo 9 1 (1.7388), G5-12CrMo 10 1 (1.7389)

ASTM: A387 gr. 9, A335 gr. 9, A234 gr. WP9 (fittings), A199 gr. T9, A213 gr. T9, A182 gr. F9, A336 gr. F9, A217 gr. C12

WELDING & PWHT

Given the hardness of the material in its deposited state (up to 450 HV) and the poor fracture resistance of the martensitic microstructure, preheating and a minimum interpass temperature of 200 °C are required to prevent hydrogen-induced cracking. By using well-controlled electrodes, the weld metal can maintain hydrogen levels below 5 ml/100 g. For TIG welds and particularly for root TIG passes, preheating below 150 °C may be acceptable. During the welding process, transformation might not complete between 200-350 °C; hence, partial cooling to about 150 °C is recommended before direct transfer to post weld heat treatment (PWHT), followed by non-destructive examinations (NDE). If PWHT is performed after full cooling and NDE, the preheat temperature must be adequately maintained according to thickness, to facilitate hydrogen dispersion. This precaution is less critical for solid wire TIG and MAG processes. PWHT for weld tempering is usually performed between 705-780 °C (as indicated, for example, by ASME B31.3 between 705-760 °C). The minimum recommended holding time is two hours. For castings, the minimum recommended PWHT temperature is slightly lower, with the possibility of dropping to 670 °C.



The information contained in this technical data sheet is provided for information purposes only, based on data believed to be reliable at the date of publication, and does not constitute a warranty or contractual commitment. Actual performance may vary depending on operating and application conditions; it is the user's responsibility to verify the suitability of the product for the intended application. The manufacturer disclaims any liability for errors, omissions, or improper use. For the latest version, please refer to www.daikowelding.com.

V 01/2024

2 / 2