



DAIKOWT 308H

GTAW

AUSTENITIC STAINLESS STEELS
308H

DESCRIPTION

Rod for 304/304H materials used at high temperatures

Rod developed for welding 18/10 stainless steels intended for high temperature service. The carbon content ranging from 0.04% to 0.08% provides greater resistance to high temperatures. These rods are suitable for welding thick sections (>12 mm) of 321H and 347H, preventing heat affected zone (HAZ) cracking during use, which is typical for these grades. The main applications concern the petrochemical sector and chemical processing plants, with typical service temperatures from 400 °C to 800 °C.

SPECIFICATIONS

EN ISO 14343-A	W 19 9 H	AWS A5.9	ER308H
Shielding	11	Positions	PA, PB, PC, PD, PE, PF
Current	DC-	Packaging Type	5kg carton tube

ASME QUALIFICATIONS

FERRITE

PREN

F-No (QW432)	6	2-8 FN	20.33
A-No (QW442)	8		

CHEM. COMP. %

DEFAULT

MECHANICAL PROPERTIES

MIN. PER STANDARD

PRODUCT

C	0.05	Tensile strength R_m MPa	550	630
Mn	1.8	Yield strength $R_{p0.2}$ MPa	350	450
Ni	9.5	Elongation A ($L_0=5d_0$) %	30	40
Cr	20	Impact Charpy ISO-V	-	100J @ -20°C
P	0.015	Impact Charpy ISO-V	-	-
S	0.002			
Mo	0.1			
Si	0.4			
Cu	0.1			
		WELDING PARAMETERS	1.6 mm	2.4 mm
		Ampere	80A - 100A	110A - 160A
		Voltage	-	-
		Packaging	Ø 1,0÷4,0 mm	Ø 1,0÷4,0 mm
		Packaging Type	5kg carton tube	5kg carton tube





308H

DESCRIPTION

AUSTENITIC STAINLESS STEELS

308H

APPLICATION

308H consumables are specifically designed for applications involving unstabilized 18Cr-10Ni austenitic stainless steels, offering high resistance to elevated temperatures and oxidation. These steels and weld metal have a carefully controlled carbon content between 0.04% and 0.08%. The levels of chromium (Cr) and nickel (Ni) in the weld metal are kept low, and the ferrite is regulated to minimize brittleness due to sigma phase formation. Minor elements and impurities, both beneficial and harmful, are controlled to optimize high-temperature properties. It is crucial that these consumables exclude components containing bismuth, ensuring a Bi level below 0.002% as required by API 582 standards. 308H consumables are also recommended for welding stabilized grades 321H or 347H thicker than 12 mm, preventing cracking in the heat-affected zone (HAZ) and low ductile fracture resistance to creep when using 347 weld metal. It is important to note that some standards suggest the use of 16-8-2 type alloys for these steels, including 304H. 308H is widely used in petrochemical and chemical processing plants, particularly in the construction of cyclones and transfer lines used to recirculate the catalyst in catalytic crackers (cat crackers) operating between 400 °C and 815 °C. Preheat is not required; the maximum interpass temperature is 250 °C. No post-weld heat treatment (PWHT) is required.

ALLOY TYPE

High carbon 308 austenitic stainless steels.

MICROSTRUCTURE

Austenite with delta ferrite controlled 2-8FN.

MATERIALS

For 304/304H materials used at elevated temperatures.

EN W.Nr.: 1.4948 (X 6 CrNi 18 11)

ASTM: 304H, A351 Gr CF10, CF8

UNS: S30409

