



DAIKOWT 385

GTAW

SUPERAUSTENITIC STEELS
904L

DESCRIPTION

Welding rod for fully austenitic 904L alloy

Full rod in copper-chromium-nickel-molybdenum alloy resistant to corrosion for welding austenitic stainless steel alloys with 20% cr, 25% ni, 5% mo, 1.5% cu, and low c content. The welding metal has good resistance to stress corrosion and intergranular corrosion, and shows excellent resistance to attack in non-oxidizing acids. The resistance to pitting corrosion is better than that of normal mo steels with 18% cr-8% ni. The alloy is widely used in many applications related to the processing industry.

SPECIFICATIONS

EN ISO 14343-A	W 20 25 5 Cu L	AWS A5.9	ER385
Shielding	I1	Positions	PA, PB, PC, PD, PE, PF
Current	DC-	Packaging Type	5kg carton tube

ASME QUALIFICATIONS

		PREN
F-No (QW432)	6	34.19
A-No (QW442)	-	

CHEM. COMP. %	DEFAULT	MECHANICAL PROPERTIES	MIN. PER STANDARD	PRODUCT
C	0.01	Tensile strength R_m MPa	510	650
Mn	1.65	Yield strength $R_{p0.2}$ MPa	320	490
Ni	25	Elongation A ($L_0=5d_0$) %	25	35
Cr	20	Impact Charpy ISO-V	-	200J @ 20°C
P	0.015	Impact Charpy ISO-V	-	-
S	0.01			
Mo	4.3			
Si	0.35			
Cu	1.45			
		WELDING PARAMETERS	1.6 mm	2.4 mm
		Ampere	80A - 100A	110A - 160A
		Voltage	-	-
		Packaging	Ø 1,0÷4,0 mm	Ø 1,0÷4,0 mm
		Packaging Type	5kg carton tube	5kg carton tube



The information contained in this technical data sheet is provided for information purposes only, based on data believed to be reliable at the date of publication, and does not constitute a warranty or contractual commitment. Actual performance may vary depending on operating and application conditions; it is the user's responsibility to verify the suitability of the product for the intended application. The manufacturer disclaims any liability for errors, omissions, or improper use. For the latest version, please refer to www.daikowelding.com.



904L

DESCRIPTION

SUPERAUSTENITIC STEELS

904L

APPLICATION

This consumable is designed to provide a fully austenitic low-carbon weld metal, enriched with molybdenum and copper. It is renowned for its excellent corrosion resistance in acidic environments, such as sulfuric and phosphoric, as well as in other types of both inorganic and organic acids. However, it is not the ideal choice for environments with concentrated nitric acid. For applications requiring chloride pitting resistance, the use of nickel-based over-alloyed weld metals, such as Alloy 625, is recommended. It is the preferred weld metal for certain low-alloy austenitics, such as Creusot UHB 34L and UHB 734L, especially when used with wet-process phosphoric acid. Typical applications include tanks and process vessels, piping systems, agitators, and rotors, as well as cast pumps and valves used for the production of fertilizers, phosphoric, sulfuric, and acetic acid. It is also suitable for brackish and marine environments and in some offshore applications, such as overlays on mild and low-alloy steels. No preheat or post-weld heat treatment (PWHT) is necessary; however, it is essential to control the interpass temperature up to a maximum of 150 °C, paying particular attention to the heat input, especially when using large diameter SMAW electrodes.

ALLOY TYPE

904L is a nominally 20%Cr-25%Ni-5%Mo-2%Cu alloy with good corrosion resistance.

MICROSTRUCTURE

In the as-welded condition the weld metal microstructure is fully austenitic.

MATERIALS

Suitable for copper-free variants of the listed alloys and also to overmatch leaner alloys such as 317L, 317LN, 317LM, 317LMN, 1.4439, 1.4440 and 531726.

EN W.Nr.: 1.4505 (X4NiCrMoCuNb20-18-2), 1.4506 (X5NiCrMoCuTi 20-18), 1.4536 (GX2NiCrMoCuN25-20), 1.4539 (X1CrNiMoCuN25-20-5), 1.4585 (G-X7CrNiMoCuNb1818), 1.4500 (G-X7NiCrMoCuNb2520)

ASTM: N08904

PROPRIETARY: Uddelholm 904L (voestalpine), 2RK65 (Sandvik), Cronifer 1925LC (VDM), 254SLX (Outokumpu), Uranus® B6, B6M (Industeel)



The information contained in this technical data sheet is provided for information purposes only, based on data believed to be reliable at the date of publication, and does not constitute a warranty or contractual commitment. Actual performance may vary depending on operating and application conditions; it is the user's responsibility to verify the suitability of the product for the intended application. The manufacturer disclaims any liability for errors, omissions, or improper use. For the latest version, please refer to www.daikowelding.com.

V 01/2024

2 / 2