



# G-TECH 1025

SMAW

COBALT ALLOYS  
Gr. 25

## DESCRIPTION

### Hardfacing electrode with rutile-basic coating

This electrode deposits a cobalt-based alloy, with the addition of chromium, tungsten and nickel to achieve excellent resistance to high temperatures and oxidation as well as sulphiting. It can be used in high temperature oxidizing environments, with operating temperatures up to 1093°C. The material also has good wear and abrasion resistance. This combination of characteristics makes this wire the ideal material for applications in the aeronautical and aerospace sectors, but also for land-based gas turbines.

## SPECIFICATIONS

EN ISO 14700	E Z Co1 (L 605)	Shielding	-
Positions	PA, PB, PC, PD, PF	Current	DC+
Packaging Type	Carton box		

## HARDNESS

220HB

CHEM. COMP. %	DEFAULT
C	0.1
Mn	1.5
Ni	10
Cr	20
Si	1
Fe	3
W	15

## WELDING PARAMETERS

	2.5 mm	3.2 mm	4.0 mm
Ampere	80A - 120A	100A - 140A	150A - 200A
Voltage	-	-	-
Packaging	pcs/kg	pcs/kg	pcs/kg
Packaging Type	Carton box	Carton box	Carton box

## ANTI-WEAR CHARACTERISTICS

Adhesive wear	▲ ▲ ▲ ▲ ▲
Abrasive wear	▲ ▲ ▲ ▲ ▲
Impact	▲ ▲ ▲ ▲ ▲
Corrosion	▲ ▲ ▲ ▲ ▲
Heat	▲ ▲ ▲ ▲ ▲

## NOTES

Pcs/kg is indicative, actual number may vary ± 5%.



The information contained in this technical data sheet is provided for information purposes only, based on data believed to be reliable at the date of publication, and does not constitute a warranty or contractual commitment. Actual performance may vary depending on operating and application conditions; it is the user's responsibility to verify the suitability of the product for the intended application. The manufacturer disclaims any liability for errors, omissions, or improper use. For the latest version, please refer to [www.daikowelding.com](http://www.daikowelding.com).



# Gr. 25

DESCRIPTION

COBALT ALLOYS  
Gr. 25

## APPLICATION

This filler metal is a variant of the rolled L605 alloy, renowned for its excellent resistance to thermal fatigue. It is ideal for the restoration and rebuilding of tools used in hot steel processing, such as shears and punches used in the steel industry. The non-magnetic welding metal offers first-rate mechanical strength and maintains good oxidation resistance up to 980 °C. It demonstrates excellent resistance to sulfidation and adequate wear and elongation resistance in metal-to-metal bonds. It also stands out for its resistance to "metal-to-metal" corrosion, abrasion, cavitation, and high-impact at elevated temperatures. It effectively resists oxidation and reducing atmospheres up to 1150 °C. Due to its notable impact resistance, it is widely used for filling molds and dies for hot forming. Its applications extend to the petrochemical sector, high-pressure steam control valves, a wide range of valves, cutting blades, as well as for refilling turbine blades, extrusion molds, dies and forging tools, furnace components, and tools for hot steel processing.

## ALLOY TYPE

Cobalt-based alloy with additions of chromium, tungsten and nickel for excellent high temperature strength and oxidation resistance

## MICROSTRUCTURE

Chromium and tungsten carbides in an austenitic type matrix.

## MATERIALS

It is used for rebuilding and/or hardfacing of tools that work hot steel, such as scissors, punches, etc. for the steel industry.

## WELDING & PWHT

Before welding, it is essential to thoroughly clean the joint surface and adjacent area. Remove all traces of grease, oil, marker marks, sulfur compounds, and other contaminants. It is important to avoid contact with copper or copper-containing materials in the joint area. Preferably, the alloy should be in the solution annealed condition during welding, although this is not strictly necessary. Preheating is usually not required as long as the base metal exceeds 0 °C. Interpass temperatures must remain low. If necessary, auxiliary cooling methods may be employed between passes, provided they do not introduce contaminants. Generally, no post-weld heat treatment is required.

