



# G-TECH 107/S

SMAW

CARBON STEELS  
STRUCTURAL STEEL

## DESCRIPTION

### Double coated rutile-basic coated electrode

Special electrode for welding medium-heavy carpentry and pipes, welds in all positions even on painted and galvanized surfaces. Suitable for positional welds, except vertical down. It ensures a very smooth bead appearance and excellent weldability with easily detachable glassy slag and good bead appearance. The deposit is crack free even when impurities are present. Ease of slag removal reduces post-welding cleaning operations to a minimum.

## SPECIFICATIONS

EN ISO 2560-A	E 42 4 B 12 H10	AWS A5.1	E7016
Shielding	-	Positions	PA, PB, PC, PD, PE, PF
Current	AC, DC+	Packaging Type	Carton box and dry pack

## ASME QUALIFICATIONS

F-No (QW432)	4
A-No (QW442)	1

CHEM. COMP. %	DEFAULT	MECHANICAL PROPERTIES	MIN. PER STANDARD				PRODUCT
C	0.08	Tensile strength R <sub>m</sub> MPa	490				500
Mn	1.1	Yield strength R <sub>p0.2</sub> MPa	420				450
Ni	0.02	Elongation A (L <sub>0</sub> =5d <sub>0</sub> ) %	22				22
Cr	0.03	Impact Charpy ISO-V	27J @ -40°C				47J @ -40°C
Mo	0.02	Impact Charpy ISO-V	-				-
Si	0.45						
Ti	0.02						
		WELDING PARAMETERS	2.5 mm	3.2 mm	4.0 mm	5.0 mm	
Ampere			50A - 80A	80A - 120A	110A - 160A	160A - 200A	
Voltage			-	-	-	-	
Packaging			50 pcs/kg	31 pcs/kg	20 pcs/kg	10 pcs/kg	
Packaging Type			Carton box and dry pack	Carton box and dry pack	Carton box and dry pack	Carton box and dry pack	

## NOTES

Pcs/kg is indicative, actual number may vary ± 5%.





# STRUCTURAL STEEL

DESCRIPTION

CARBON STEELS  
STRUCTURAL STEEL

## APPLICATION

Carbon-manganese steels (C-Mn) are the backbone for a wide range of applications in the structural engineering industry. Welding of these steel structures can be successfully achieved provided the material composition is known, appropriate precautions are adopted, and qualified procedures are followed. Weldability varies based on the type of C-Mn steel, and there is a risk of defects such as hydrogen cracking, solidification cracking, or reheat cracking, which depend on specific operating conditions. The proposed consumables offer effective resistance to these issues, emphasizing the importance of a carefully defined welding process. Preheating and post-weld heat treatment (PWHT) are not always necessary, but their adoption depends on the type and thickness of the base material. The desired mechanical properties in the welded joint can be achieved using appropriate consumables. However, the complex structural transformations that occur during the welding thermal cycle require careful evaluation of critical parameters such as the toughness and hardness of the heat-affected zone (HAZ).

## ALLOY TYPE

Consumables for welding mild and C-Mn steels of 340-510MPa tensile strength.

## MICROSTRUCTURE

Predominantly ferrite.

## MATERIALS

Carbon and carbon-manganese steels encompass a wide range of structural and pressure-grade materials commonly used in construction, mechanical engineering, and industrial plant applications. Among the EN-standardized grades are non-alloy structural steels intended for general use, known for their good weldability and progressively higher mechanical strength. The "P" grades, on the other hand, are pressure vessel steels typically used in boilers and heat exchangers. Equivalent ASTM specifications cover a similar scope of applications and are widely adopted internationally for structural components, piping, and fittings exposed to pressure or high temperatures. Lastly, API specifications are typical of the oil & gas sector, particularly for the production of pipelines used in hydrocarbon transport, offering increasing levels of mechanical strength and specific performance requirements.

**EN W.Nr.:** S 235 JR, S 235 JO, S 235 J2+N, S 275, S 275 JO, S 275 J2+N, S 355 JR, S 355 JO, S 355 J2+N, S 355 K2+N, P 235 GH, P 265 GH, P 295 GH

**ASTM:** A36, A106 gr. A, A106 gr. B, A106 gr. C, A139, A210 gr. A1, A210 gr. C, A234 gr. WPB, A334 gr. 1, A216 gr. WCA, A216 gr. WCB, A216 gr. WCC

**API:** A, B, X42, X52, X60

