



G-TECH 2594B

SMAW

DUPLEX - SUPERDUPLEX
2507

DESCRIPTION

Basic coated electrode for Superduplex ferritic-austenitic stainless steels

Offshore applications exploit the high resistance to pitting (typical pitting resistance equivalent number "PREn" of 43) and stress corrosion cracking in seawater. It is also highly resistant to caustic alkalis and phosphoric acid. Widely used in oil and gas production and process. Its basic coating ensures excellent positional welding characteristics with good gap bridging ability. The weld pool and slag are easy to control and facilitate the achievement of a clean bead surface even in narrow preparations and in root pass.

SPECIFICATIONS

EN ISO 3581-A	E 25 9 4 N L B 42	AWS A5.4	E2594-15
Shielding	-	Positions	PA, PB, PC, PD, PE, PF
Current	DC+;	Packaging Type	Carton box

ASME QUALIFICATIONS

	FERRITE	PREN
F-No (QW432)	5 % 30-60	42.54
A-No (QW442)	-	

CHEM. COMP. %	DEFAULT	MECHANICAL PROPERTIES	MIN. PER STANDARD	PRODUCT
C	0.035	Tensile strength R _m MPa	620	850
Mn	0.9	Yield strength R _{p0.2} MPa	550	630
Ni	9.5	Elongation A (L ₀ =5d ₀) %	18	22
Cr	25.5	Impact Charpy ISO-V	-	40J @ -40°C
N	0.24	Impact Charpy ISO-V	-	-
P	0.02			
S	0.01			
Mo	4			
Si	0.7			
Cu	0.3			

WELDING PARAMETERS	2.5 mm	3.2 mm	4.0 mm
Ampere	50A - 80A	70A - 110A	100A - 160A
Voltage	-	-	-
Packaging	56 pcs/kg	30 pcs/kg	19 pcs/kg
Packaging Type	Carton box	Carton box	Carton box

NOTES

Rutile-basic (-16) version available upon request. Pcs/kg is indicative, actual number may vary ± 5%.



The information contained in this technical data sheet is provided for information purposes only, based on data believed to be reliable at the date of publication, and does not constitute a warranty or contractual commitment. Actual performance may vary depending on operating and application conditions; it is the user's responsibility to verify the suitability of the product for the intended application. The manufacturer disclaims any liability for errors, omissions, or improper use. For the latest version, please refer to www.daikowelding.com.



2507

DESCRIPTION

DUPLEX - SUPERDUPLEX
2507

APPLICATION

Super duplex stainless steel pipes, plates, fittings, and forgings have a microstructure composed of approximately 50% austenite and 50% ferrite matrix. This combination, along with the alloy composition, offers several key benefits: - high strength compared to standard austenitic steels like type 316L; - excellent overall corrosion resistance in a wide range of environments; - high resistance to chloride-induced stress corrosion cracking (CSCC); - remarkable resistance to pitting attack in environments containing chlorides, such as seawater. These characteristics make super duplex alloys ideal for continuously evolving applications in the ****offshore oil/gas, chemical, and petrochemical industry.**** They are frequently used in piping systems, flow lines, risers, manifolds, and more.

ALLOY TYPE

25%Cr ferritic-austenitic superduplex stainless steels.

MICROSTRUCTURE

Austenite-ferrite duplex microstructure in AW or solution annealed condition with an approximate 30- 60% ferrite level, depending on heat cycle conditions.

MATERIALS

EN W.Nr.: 1.4410 (X2CrNiMoN25-7-4)

ASTM: A182 F53, A182 F55, A890 Gr5A, A890 Gr6A

UNS: S32750, S32760, J93404

PROPRIETARY: SAF 2507 (Sandvik), Uranus® 47N (Industeel)

WELDING & PWHT

Generally, preheating is not required. The interpass temperature is set to a maximum of 150 °C. A heat input range of 1.0-2.0 kJ/mm, depending on the thickness of the material, is acceptable, with many codes specifying a maximum limit of 1.5 or 1.75 kJ/mm. Although welds on duplex stainless steels are almost always left as-welded, major repairs on castings are generally carried out in a solution-treated condition. Industry practices suggest that excellent mechanical properties can be obtained through water quenching at 1120 °C, held for 3-6 hours.

