



# G-TECH 307B

SMAW

AUSTENITIC STAINLESS STEELS  
307

## DESCRIPTION

### Basic coated electrode for dissimilar joints and buffer layers

For tough buffer and intermediate layers for cladding of rails and switches, valve seats and in hydropower plants. The weld metal offers exceptionally high ductility and elongation together with outstanding crack resistance. Resistance to hot cracking is provided by the high manganese content. Good resistance to embrittlement when operating at service temperatures from -100°C up to 650°C. The weld metal work hardens and offers good resistance to cavitation. Ease of slag removal reduces post-welding cleaning operations to a minimum.

## SPECIFICATIONS

EN ISO 3581-A	E 18 9 Mn Mo	AWS A5.4	E307-15
Shielding	-	Positions	PA, PB, PC, PD, PE, PF
Current	DC+;	Packaging Type	Carton box

## ASME QUALIFICATIONS

## FERRITE

## PREN

F-No (QW432)	5	-5 FN	20.98
A-No (QW442)	-		

## CHEM. COMP. %

## DEFAULT

## MECHANICAL PROPERTIES

## MIN. PER STANDARD

## PRODUCT

C	0.09	Tensile strength R <sub>m</sub> MPa	500	600
Mn	4.5	Yield strength R <sub>p0.2</sub> MPa	350	400
Ni	9.8	Elongation A (L <sub>0</sub> =5d <sub>0</sub> ) %	25	35
Cr	19	Impact Charpy ISO-V	-	80J @ 20°C
Mo	0.6	Impact Charpy ISO-V	-	-
Si	0.8			

## WELDING PARAMETERS

## 2.5 mm

## 3.2 mm

## 4.0 mm

## 5.0 mm

Ampere	50A - 80A	80A - 110A	110A - 150A	150A - 200A
Voltage	-	-	-	-
Packaging	56 pcs/kg	28 pcs/kg	19 pcs/kg	12 pcs/kg
Packaging Type	Carton box	Carton box	Carton box	Carton box

## NOTES

Pcs/kg is indicative, actual number may vary ± 5%.





# 307

DESCRIPTION

AUSTENITIC STAINLESS STEELS

307

## APPLICATION

Applications for this subfamily include the welding of different materials such as mild steels, stainless steels, hardenable and ballistic steels, both among themselves and with other metals, with or without the need for preheating. The high manganese content ensures excellent dilution tolerance and resistance to hot cracking, unlike ballistic steels and type 309, which require a high ferrite content. In some situations, this material can effectively replace those with high nickel content in joints between cast iron and stainless steels. Welds subjected to post-weld heat treatment (PWHT) maintain good ductility and toughness down to -50°C. Additionally, it offers moderate resistance to scale formation at temperatures up to 850°C. It is ideal as a cushion layer for welding or repairing steels with 13% Mn used in crushing plants or earthmoving equipment. It is also recommended as an intermediate layer on cast iron before a hard facing. This consumable is designed for surfacing operations with hardening between 200 and 400 HV, and is well-suited for repairing alloy rails, sleepers, and crossings, avoiding preheating. However, the hardening rate is lower compared to steel with 13% Mn, and overlays beyond a single layer may collapse under heavy rolling loads.

## ALLOY TYPE

Strong tough austenitic weld metal composition for dissimilar joints and buffer layers.

## MICROSTRUCTURE

Consists of austenite with approximately 5FN.

## MATERIALS

Dissimilar combinations of C-Mn, stainless, hardenable, wear-resistant and armour steels. Suitable for 13% Mn steel also known as Hadfield steel.

## WELDING & PWHT

In general, preheating is not necessary, unless working with very thick sections. However, in-service conditions require consideration of Heat-Affected Zone (HAZ) properties for high-carbon hardenable steels. When welding steels with 13% Mn, it is essential to minimize brittleness and the risk of cracking by keeping the workpiece cool. Therefore, the following precautions must be applied: no preheating, controlling interpass temperature to a maximum of 150°C, low heat input, making small weld beads, and cooling with water if necessary.

