



# G-TECH 309LB

SMAW

AUSTENITIC STAINLESS STEELS  
309L

## DESCRIPTION

### Basic coated low carbon electrode for dissimilar joining and buffer layer

Its basic coating ensures excellent positional welding characteristics with good gap bridging ability. The weld pool and slag are easy to control and facilitate the achievement of a clean bead surface even in narrow preparations and in root pass. Ease of slag removal reduces post-welding cleaning operations to a minimum. These electrodes are mainly used under high dilution conditions, particularly dissimilar welds between stainless and C-Mn steels. Also overlays on C-Mn steel or low alloy steel and for joining clad plate.

## SPECIFICATIONS

EN ISO 3581-A	E 23 12 L B 42	AWS A5.4	E309L-15
Shielding	-	Positions	PA, PB, PC, PD, PE, PF
Current	DC+;	Packaging Type	Carton box

ASME QUALIFICATIONS	FERRITE	PREN	HARDNESS	
F-No (QW432)	5	8-15 FN	23.5	85HRB
A-No (QW442)	8			

CHEM. COMP. %	DEFAULT	MECHANICAL PROPERTIES	MIN. PER STANDARD	PRODUCT		
C	0.035	Tensile strength $R_m$ MPa	510	560		
Mn	1.7	Yield strength $R_{p0.2}$ MPa	320	400		
Ni	12.5	Elongation A ( $L_0=5d_0$ ) %	25	30		
Cr	23.5	Impact Charpy ISO-V	-	50J @ 20°C		
P	0.02	Impact Charpy ISO-V	-	-		
S	0.01					
Si	0.8					
Cu	0.1					
		WELDING PARAMETERS	2.5 mm	3.2 mm	4.0 mm	5.0 mm
		Ampere	50A - 80A	80A - 110A	110A - 150A	160A - 210A
		Voltage	-	-	-	-
		Packaging	56 pcs/kg	28 pcs/kg	19 pcs/kg	12 pcs/kg
		Packaging Type	Carton box	Carton box	Carton box	Carton box

## NOTES

Pcs/kg is indicative, actual number may vary  $\pm$  5%.



The information contained in this technical data sheet is provided for information purposes only, based on data believed to be reliable at the date of publication, and does not constitute a warranty or contractual commitment. Actual performance may vary depending on operating and application conditions; it is the user's responsibility to verify the suitability of the product for the intended application. The manufacturer disclaims any liability for errors, omissions, or improper use. For the latest version, please refer to [www.daikowelding.com](http://www.daikowelding.com).



# 309L

## DESCRIPTION

AUSTENITIC STAINLESS STEELS

309L

### APPLICATION

**\*\*Bearing layers and claddings on steels\*\*:** Ideal for overlays on carbon-manganese steels, mild or low alloy steels, and for joining clad plates in 304L/321. Successive layers are applied with electrodes selected to match the cladding, such as 308L or 347. **\*\*Dissimilar connections\*\*:** Thanks to its tolerance to dilution, it is used to join stainless steels like 410, 304L, 321, and 316L with mild and low alloy steels for reinforcements, brackets, and other accessories. Not suitable for service temperatures above 400 °C. It is also suitable for welding 12% Cr ferritic steels, such as Cromwell 3CR12, both among themselves and with other steels. **\*\*Similar metal joints\*\*:** Wrought and cast steels, type 23Cr-12Ni (e.g., ASTM 309 and CH8, BS 309S24 and 309C30), can be welded when corrosion resistance below 400 °C is required. For high-temperature structural applications, a welding metal with a higher carbon content and reduced ferrite is necessary. Preheating and interpass temperatures depend on the hardenability of the base material. As a guide, no preheating is necessary for mild steels; on hardenable ones, the temperature can reach up to 250 °C.

### ALLOY TYPE

24%Cr-13%Ni (309L) austenitic stainless for dissimilar joint buffer layers etc.

### MICROSTRUCTURE

Austenite with ferrite in the range 8-20FN. GMAW tends to have lower ferrite (8-15 FN) than the MMA and FCW consumables.

### MATERIALS

Mainly used under high dilution conditions, particularly dissimilar welds between stainless and CMn steels.

