



G-TECH 310B

SMAW

SUPERAUSTENITIC STEELS
310

DESCRIPTION

Basic coated electrode for 25%Cr-20%Ni (310) stainless steels

This electrode is used to weld 310 fully austenitic stainless steels. Applications include heat shields, furnace and boiler parts, heat exchanger and ducting for the good resistance to high temperature oxidation of these alloys. Also suitable for dissimilar joints, buffer layers, weld overlay and cryogenic applications. Ease of slag removal reduces post-welding cleaning operations to a minimum leaving a concave bead with minimal ripple as well as a smooth and clean weld profile.

SPECIFICATIONS

EN ISO 3581-A	E 25 20 B 42	AWS A5.4	E310-15
Shielding	-	Positions	PA, PB, PC, PD, PE, PF
Current	DC+;	Packaging Type	Carton box

ASME QUALIFICATIONS

		PREN
F-No (QW432)	5	26.66
A-No (QW442)	-	

CHEM. COMP. %	DEFAULT	MECHANICAL PROPERTIES	MIN. PER STANDARD			PRODUCT
C	0.1	Tensile strength R_m MPa	550			600
Mn	2	Yield strength $R_{p0.2}$ MPa	350			400
Ni	21	Elongation A ($L_0=5d_0$) %	20			30
Cr	26	Impact Charpy ISO-V	-			80J @ 20°C
P	0.02	Impact Charpy ISO-V	-			-
S	0.01					
Mo	0.2					
Si	0.6					
Cu	0.1					
		WELDING PARAMETERS	2.5 mm	3.2 mm	4.0 mm	5.0 mm
		Ampere	50A - 80A	80A - 110A	110A - 150A	150A - 200A
		Voltage	-	-	-	-
		Packaging	56 pcs/kg	29 pcs/kg	19 pcs/kg	12 pcs/kg
		Packaging Type	Carton box	Carton box	Carton box	Carton box

NOTES

Pcs/kg is indicative, actual number may vary \pm 5%.



The information contained in this technical data sheet is provided for information purposes only, based on data believed to be reliable at the date of publication, and does not constitute a warranty or contractual commitment. Actual performance may vary depending on operating and application conditions; it is the user's responsibility to verify the suitability of the product for the intended application. The manufacturer disclaims any liability for errors, omissions, or improper use. For the latest version, please refer to www.daikowelding.com.



310

DESCRIPTION

SUPERAUSTENITIC STEELS

310

APPLICATION

The product is primarily used for welding 25% Cr-20% Ni (310) alloys, which can be wrought or cast, and contain up to 0.25% carbon. To ensure maximum resistance to cracking and microfissures during solidification, the manganese content in the welding metal is increased to 2-5%. The high alloy content of type 310 provides excellent oxidation resistance up to maximum temperatures of about 1200 °C, making it ideal for heat shields, furnace components, and ducts. These consumables are also suitable for mixed welds and dissimilar joints, including those where PWHT application is necessary. However, it is important to consider that the relatively high thermal expansion coefficient may cause thermal fatigue in transition joints subjected to thermal cycling. In such situations, the use of nickel-based consumables is generally recommended. Further applications include cushioned layers and overlays. The fully austenitic welding metal is suitable for specialized applications requiring low magnetic permeability (typically <1.01). Additionally, 310 welding metals intrinsically withstand temperatures down to -196 °C, making them suitable for cryogenic installations. Preheating is not necessary. It is preferable to maintain the interpass temperature below 150 °C and heat input below 1.5 kJ/mm; this is crucial especially for processes with high heat input, such as SAW.

ALLOY TYPE

25%Cr-20%Ni (310) stainless steel.

MICROSTRUCTURE

Fully austenitic.

MATERIALS

EN W. N.: 1.4826 (GX40CrNiSi22-10), 1.4828 (X15CrNiSi2012), 1.4837 (GX40CrNiSi25-12), 1.4840 (GX15CrNi2520), 1.4841 (X15CrNiSi25-21), 1.4846 (X 40 CrNi 25-21), 1.4847 (X 8 CrNiAlTi 20-20), 1.4848 GX40CrNiSi25-20), 1.4335 (X1CrNi25-21), 1.4435 (X2CrNiMo18-14-3), 1.4446 (X1CrNiMoN22-25-3), 1.4547 (X3CrNiMoTi25-25)

ASTM: 310, 310S, CK20, 305, 314, 725LN, 316L

UNS: S31000, S31008, S31050, S31603

