



G-TECH 323

SMAW

CAST IRON
NiFe-CI

DESCRIPTION

Electrode with basic-graphite coating and 55% Nickel rod

Nickel/iron based electrode for welding and repair of graphitic and mechanical cast irons. Also suitable for joining cast iron with steel in general. Its main applications are in the repair and maintenance of machine tool bases, engine blocks, casting defects elimination, pumps, cylinders, pistons. Making small beads and hammering the deposit are recommended to avoid cracks. Castings containing phosphorus levels higher than normal, approximately 0.20%, are more readily welded using these electrodes than with an electrode of the ENi-CI classification.

SPECIFICATIONS

EN ISO 1071	E C NiFe-CI 1	AWS A5.15	ENiFe-CI
Shielding	-	Positions	PA, PB, PC, PD, PF
Current	DC+	Packaging Type	Carton box

HARDNESS

190HB - 210HB

CHEM. COMP. %	DEFAULT	MECHANICAL PROPERTIES	MIN. PER STANDARD			PRODUCT
C	1	Tensile strength R_m MPa	400			490
Mn	0.8	Yield strength $R_{p0.2}$ MPa	300			340
Ni	55	Elongation A ($L_0=5d_0$) %	8			10
S	0.02	Impact Charpy ISO-V	-			-
Si	0.7	Impact Charpy ISO-V	-			-
		WELDING PARAMETERS	2.5 mm	3.2 mm	4.0 mm	
		Ampere	70A - 90A	90A - 120A	120A - 140A	
		Voltage	-	-	-	
		Packaging	pcs/kg	pcs/kg	pcs/kg	
		Packaging Type	Carton box	Carton box	Carton box	

NOTES

Pcs/kg is indicative, actual number may vary \pm 5%.



The information contained in this technical data sheet is provided for information purposes only, based on data believed to be reliable at the date of publication, and does not constitute a warranty or contractual commitment. Actual performance may vary depending on operating and application conditions; it is the user's responsibility to verify the suitability of the product for the intended application. The manufacturer disclaims any liability for errors, omissions, or improper use. For the latest version, please refer to www.daikowelding.com.



NiFe-CI

DESCRIPTION

CAST IRON

NiFe-CI

APPLICATION

The NiFe alloy is designed to weld various types of cast iron, with a particular focus on spheroidal graphite (SG), nodular or ductile cast irons, as well as some special cast iron alloys. This alloy provides an optimal combination of strength, ductility, and toughness, while ensuring good workability. NiFe consumables are versatile and can also be used on certain high-alloy austenitic cast irons (Ni-Resist). For flake graphite cast iron grades, preheating of 300-350 °C is recommended; however, for SG grades, a buttering procedure using low heat input and low temperature techniques is advised to avoid hot cracking in the heat affected zones (HAZ). It is important to note that Ni-Hard martensitic and white cast irons are generally unweldable due to their high susceptibility to cracking. NiFe consumables are also ideal for creating transition joints between cast iron and cast steels or between cast iron and mild/low-alloy steels. Common components include ****machine bases, pump bodies, engine blocks, gears, and gearbox housings****.

ALLOY TYPE

Nominally Fe-40% Ni alloy for the repair and joining of cast iron.

MICROSTRUCTURE

The structure depends on the chemical composition and the speed of solidification and subsequent cooling down.

MATERIALS

The NiFe weld metals produce higher strength than the pure nickel cast iron types and are therefore preferable for dissimilar joints, higher strength cast irons and spheroidal graphite cast irons.

EN W.Nr.: 1563:2018 Spheroidal graphite cast irons, 1562:2019-06 Malleable cast irons

ASTM: A602, A47, A338, A220

WELDING & PWHT

In many cases, welding can be performed without preheating; however, for heavy multi-pass deposits or joints with high constraints, preheating between 150-250 °C may be necessary. Prior to welding, surfaces must be prepared by gouging and/or grinding, minimizing heat input to prevent crack propagation. It is essential that the area to be welded is as free from contaminants like sand, oil, grease, paint, or rust as possible. Preheating can be helpful in eliminating oil impregnated in castings to be repaired. If proceeding without preheat, it is preferable to limit the width of the HAZ using low heat input and low interpass temperature welding techniques. Using a fractional welding technique can be advantageous. For welding of thicker sections or with high constraints, preheating in the range of 150-250 °C might be necessary. Additionally, light peening to reduce contraction stresses can be beneficial, but it's crucial not to compromise the ductility of the weld metal. Buttering of the joining faces or sides of the repair cavity is also recommended before completion, regardless of the preheat applied. After welding, gradual cooling of the piece, with insulation if necessary, is highly recommended.

